

E-ISSN: 2708-0021  
P-ISSN: 2708-0013  
[www.actajournal.com](http://www.actajournal.com)  
AEZ 2025; 6(1): 17-19  
Received: 15-11-2024  
Accepted: 18-12-2024

**Dr. K Sujatha**  
Lecturer in Zoology, S.G.A.  
Government Degree College,  
Yallamanchilli, Anakapalli,  
Andhra Pradesh, India

## Study on the antibacterial effect of crab shell extract on klebsiella pneumoniae and proteus mirabilis

**Dr. K Sujatha**

DOI: <https://doi.org/10.33545/27080013.2025.v6.i1a.184>

### Abstract

The objective of this study was to examine the antibacterial effect of crab shell extract on *Klebsiella pneumoniae* and *Proteus mirabilis*. *K. pneumoniae* and *P. mirabilis* were isolated from urine and wound specimen and characterized using standard laboratory methods. Antibacterial susceptibility testing using crab shell extract showed that only *K. pneumoniae* were sensitive while *P. mirabilis* were resistant. Isolates of *K. pneumoniae* had varied minimal inhibitory concentration, with isolates Kp1 and Kp3 having 12.5µg/ml while isolates Kp2 had 6.25µg/ml. At a concentration of 200µg/ml of crab shell extract, the highest zone of inhibition of *K. pneumoniae* was 12mm. This figure is however low when compared with commonly used antibiotics which gave larger zones of inhibition at lower concentration.

**Keywords:** *K. pneumoniae*, *P. mirabilis*, chitin, Chitosan, cellulose.

### Introduction

Crab shell is made up of three basic components. These are; chitin, protein and calcium salts of which chitin is most important for scientific studies<sup>[9]</sup>. Chitin is a fairly completely acetylated polysaccharide in nature, being only second after cellulose<sup>[12]</sup>. It can be also be found in other animals [exoskeleton of crustacean and insects] as well as in fungi, mushrooms and yeast<sup>[2, 12]</sup>.

Chitin was first isolated by Professor Henri Bracomot, Director of the Botanical Garden in Nancy, France from the cell wall of mushrooms in 1811. It was known then as *fungine*. In 1823, Odier renamed *fungine* as chitin [meaning tunic in Greek] almost three decades before the isolation of cellulose<sup>[20]</sup>.

Chitin is a white and porous polysaccharide. It is a biopolymer composed of N-acetyl-D-glucosamine, a chemical structure very close to cellulose except that the hydroxyl group in [C<sub>2</sub>] of cellulose is being replaced by the acetamide group in chitin<sup>[20]</sup>.

Its unit are joined by -1.4 links and chains are arranged anti-parallel which combine into a highly crystalline structure, within which the sugar residue are heavily H-banded making the chains very stiff and stable<sup>[23]</sup>.

The deacetylation of Chitin produces a non-toxic biodegradable polymer of D-glucosamine known as Chitosan. It is of high molecular weight and also very similar to cellulose<sup>[20]</sup>.

Chitosan is the important derivative from crab shell extract known to have been used for several application, including domestic, agriculture and biopharmaceutical<sup>[8]</sup>.

### Application of Chitosan

Application of chitosan can be classified mainly into three categories according to the requirements on the purity of the chitosan<sup>[8]</sup>. These are;

#### Technical grade for the agricultural and waste management treatment

Chitosan has been used for seed coating, frost protection, bloom and fruit setting stimulation and protective coating for fruits and vegetables. This is because it triggers the defensive mechanism in plants and also stimulates growth<sup>[8]</sup>. It is also a known flocculating agent which is biodegradable and of natural origin hence being used to improve the effectiveness of water treatment<sup>[20]</sup>.

**Corresponding Author:**  
**Dr. K Sujatha**  
Lecturer in Zoology, S.G.A.  
Government Degree College,  
Yallamanchilli, Anakapalli,  
Andhra Pradesh, India

### Pure grade for food and cosmetics industries

Chitosan is also being used as food ingredient in Japan, Europe and USA. It is not digested by the human body, thereby acting as a fibre with the ability to reduce 20-30% the amount of cholesterol absorbed by the human body<sup>[21, 13, 14]</sup>. Also as an antimicrobial agent, it is sprayed in dilute forms on foods and fruits<sup>[20]</sup>.

### Ultra-pure grade for biopharmaceutical uses

In this field, many properties of chitosan is employed, these are; bacterostatic, immunologic, antitumor, cicatrizant, haemostatic and anticoagulant properties<sup>[1]</sup>. For example, due to its cicatrizant properties it has been used as a component in all types of dressing, surgical sutures, dental implants and in rebuilding bones and gums<sup>[15]</sup>. Chitosan is also helpful in kidney failure as it binds with toxins in the digestive tract thereby leading to their excretion<sup>[11]</sup>.

### Results and Discussion

The antimicrobial activity of crab shell extract is presented in Table 1. From the table the average minimum inhibitory concentration [MIC] of *Klebsiella pneumoniae* [Kp] was determined to be 10.42 µg/ml. Table 1 shows the activity of the 1% acetic acid used. It was observed from result that the three isolates of *Klebsiella pneumoniae* were sensitive to the crab shell extract, demonstrating the fact that the extract had antibacterial potential. Also observed is the increase in the susceptibility pattern with increase in concentration on of the extract [See Table 1]. The highest zone of inhibition [12 mm] was recorded for isolate Kp2 at 200µg/ml. This figure is however low when compared to zones of inhibition of

commonly used antibiotics, when isolates of *K. pneumoniae* were subjected to them Results showed that *Proteus mirabilis* were resistant to crab shell extract and susceptible to commonly used antibiotics


### Experimental section

#### Source of crab

Sixty crabs were obtained from Visakhapatnam city and then killed mechanically with their shells emptied of all tissue. Shells were then washed with distilled water, oven dried for 7 hours, thereafter ground into fine powder.

#### Preparation of crab shell extract

Preparation of crab shell extract consist of four fundamental steps: Deproteinization, demineralization, decolouration and deacetylation [See Figure 1]. All chemicals used during each steps were decanted and powder washed with distilled water before the next stage. 200ml of 3.5% NaOH was used to deproteinize 20g of fine powder of crab shell in a beaker at a temperature of 65 °C for 2 hours. The shells were then demineralised by adding 200ml of 1N HCL into the beaker an left for 30 mins at room temperature. Decolouration was carried out by adding 200ml of 0.315% NaOCL for 5 mins at room temperature. Finally, 200ml of 50% NaOH was used for deacetylation for 15 mins at 121 °C. After thorough washing of the powder, it was then oven dried and pH determined and found to be 5.0. 2g of extract was dissolved in 10ml of 1% acetic acid and then serially diluted into test tubes using the double fold dilution method adapted from<sup>[10]</sup> to get different concentrations/dilutions of extract.



**Fig 1:** Flow chart of preparation of crab shell extract

### Source of Microorganisms

Three isolates of *Klebsiella pneumoniae* [Kp] and two isolates of *Proteus mirabilis* [Pm] were obtained from patients with wound and urinary tract infection from the University of Benin Teaching Hospital [UBTH]. Isolates were identified based on: Cultural/Morphological characteristics, Gram staining technique and Biochemical testing [5].

### Susceptibility Testing

Seven dilutions of the crab shell extract were transferred into prepared Nutrient agar plates containing isolates using the punch-hole agar diffusion method [18] and incubated for 24 hours at 37 °C. The 1% acetic acid was also tested differently to determine if susceptibility would be as a result of the acetic present in the different dilutions.

Known concentrates of commonly used antibiotics were also tested against the clinical isolates using the disc diffusion method [3]. These antibiotics include: Ciprofloxacin [10 µg], Amoxicillin [30 µg], Augmentin [10 µg], Gentamycin [30 µg], Pefloxacin [30 µg], Tarvid [10 µg], Streptomycin [30 µg], Septrin [30 µg], Chloramphenicol [30 µg] and Sparfloxacin [10 µg]. After 24 hours of incubation, zones of inhibition were measured and recorded.

### Conclusions

In conclusion, results from this study has demonstrated the antimicrobial activity of crab shell extract as suggested by a number of researchers [17, 4, 7]. Researchers have also shown that crab shell is biocompatible with human tissues, therefore less toxic than commonly used antibiotics [16, 19]. Thus, instead of the wasteful disposal of crab shells after consuming the fleshy part, more research should be geared towards the effective usage of crab shell extract as an antimicrobial agent. This would serve as an economic advantage to the country.

### References

1. Aranaz I, Mengibar M, Harris R, Paños I, Miralles B, Acosta N, *et al.* Functional characterization of chitin and chitosan. *Current Chemical Biology*. 2009;3:203-230.
2. Badawy MEI, Rabea EI. A biopolymer chitosan and its derivatives as promising antimicrobial agents against plant pathogens and their applications in crop protection. *International Journal of Carbohydrate Chemistry*, 2011, p. 29.
3. Bauer AW, Kirby WM, Sherris JC, Turck M. Antibiotic susceptibility testing by standardized single disk method. *American Journal of Clinical Pathology*. 1966;45(4):493-496.
4. Chhabra P, Huang YW, Frank JF, Chmielewski R, Gates K. Fate of *Staphylococcus aureus*, *Salmonella enterica* serovar Typhimurium, and *Vibrio vulnificus* in raw oysters treated with chitosan. *Journal of Food Protection*. 2006;69:1600-1604.
5. Cheesbrough M. *District Laboratory Practice in Tropical Countries*. Cambridge: Cambridge University Press; 2000.
6. Emori G, Gaynes P. An overview of nosocomial infections including the role of the microbiology laboratory. *Clinical Microbiology Review*. 1993;6(4):428-442.
7. Ganan M, Carrascosa AV, Martinez-Rodriguez AJ. Antimicrobial activity of chitosan against *Campylobacter* spp. and other microorganisms and its mechanism of action. *Journal of Food Protection*. 2009;72:1735-1738.
8. Gossen NFA. *Application of Chitin and Chitosan*. Lancaster: Technomic Publishing Company, 1997.
9. Hirano S. Production and application of chitin and chitosan in Japan. In: Skjak-Braek G, Anthonsen T, Sandford P, editors. *Chitin and Chitosan: Sources, Chemistry, Biochemistry, Physical Properties and Application*. London/New York: Elsevier Applied Science, 1989, p. 37-44.
10. Ibekwe VI, Nanyere NF, Akujobi CO. Studies on antibacterial activity and phytochemical qualities of extracts of orange peels. *International Journal of Environmental Health and Human Development*. 2001;2(1):41-46.
11. Jing S, Li L, Takiguchi Y, Yamaguchi T. Effect of chitosan on renal function in patients with chronic renal failure. *Journal of Pharmaceutical Pharmacology*. 1997;49:721-723.
12. Kim JY, Kim KN, Kim JG, Kim SC, Lee WJ, Hyun CG. *In vitro* antimicrobial and antioxidant activities of chitosan oligosaccharides. *Journal of Applied Biology and Chemistry*. 2009;52(2):84-87.
13. Knorr D. Functional properties of chitin and chitosan. *Journal of Food Science*. 1982;47:593-595.
14. Knorr D. Use of chitosan polymer in food: A challenge for food research and development. *Food Technology*. 1984;38:85-87.
15. Koide SS. Chitin-chitosan: properties, benefits and risks. *Nutrition Research*. 1998;18(6):1091-1101.
16. No HK, Meyers SP, Prinyawiwatkul W, Xu Z. Applications of chitosan for improvement of quality and shelf life of foods: A review. *Journal of Food Science*. 2007;72:87-100.
17. No HK, Park NY, Lee SH, Meyers SP. Antibacterial activity of chitosans and chitosan oligomers with different molecular weights. *International Journal of Food Microbiology*. 2000;74:65-72.
18. Okwori AEJ, Okeke CI, Uzoechina A, Etukudoh NS, Amali MN, Adetunji JA, *et al.* The antibacterial potentials of *Nauclea latifolia*. *African Journal of Biotechnology*. 2008;7(10):1394-1399.
19. Raafat D, Sahl HG. Chitosan and its antimicrobial potential: A critical literature survey. *Microbial Biotechnology*. 2009;2:186-201.
20. Roberts GAF. *Chitin Chemistry*. London: Macmillan, 1992.
21. Schiller RN, Barrager E, Schauss AG, Veltmann JR, Nicolas EJ. A randomized double-blind placebo-controlled study examining the effects of a rapidly soluble chitosan dietary supplement on weight loss and body composition in overweight and mildly obese individuals. *Journal of the American Nutraceutical Association*. 2001;4:42-49.
22. Sedor J, Mulholland S. Hospital acquired UTI associated with the indwelling catheter. *Urologic Clinics of North America*. 1999;26(4):821-828.
23. Vincent JFY. Insect cuticle: A paradigm for nature composites. In: Vincent JFY, Currey JD, editors. *The Mechanical Properties of Biological Materials*. Cambridge: The University Press, 1980, p. 183-210.